

Sub D1  
a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:

steel in the range of from 20 to 50 percent by weight;

and

filler in the range of from 50 to 80 percent by weight,

the filler comprising in the range of from 10 to [100] 99 percent by weight spherical cast tungsten carbide particles having a particle<sup>size</sup> between about 16 to 40 mesh and between about 80 and 200 mesh, and tungsten carbide particles selected from the group consisting of spherical cemented, crushed cemented, crushed cast, crushed macrocrystalline, and carburized.

Bl

2. The rock bit of claim 1 comprising filler in the range of from 60 to 75 percent by weight.

3. The rock bit of claim 1 wherein the filler comprises in the range of from 20 to 50 percent by weight spherical cast tungsten carbide particles.

Sub D2  
4. (Amended) The rock bit of claim 1 wherein the filler comprises in the range of from 40 to [100] 99 percent by weight spherical cast tungsten carbide particles.

Sub D2 D3  
7. (Amended) The rock bit of claim [6] 1 wherein the filler comprises spherical cast tungsten carbide particles having a particle size between about 100 to 200 mesh.

8. (Amended) The rock bit of claim [5] 1 wherein the filler further comprises macrocrystalline tungsten carbide particles having a particle size between about 40 to 80 mesh.

Sub D3

9. A rock bit as recited in claim 1 wherein the hardfacing comprises in the range of from 10 to 90 percent by weight spherical cast tungsten carbide particles having a particle size between about 16 to 40 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 35 percent by weight of the filler material, the particles having a particle size in the range of from about 1 to 50 microns.

10. A rock bit as recited in claim 9 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical cast.

B2

11. A rock bit as recited in claim 9 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

Sub D4

12. A rock bit comprising:

- a body;
- at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone;
- a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:
  - steel in the range of from 20 to 50 percent by weight;
  - filler in the range of from 50 to 80 percent by weight,
  - the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having a particle size between about 80 to 200 mesh.

13. The rock bit of claim 12 comprising filler in the range of from 60 to 75 percent by weight.

14. The rock bit of claim 12 wherein the filler comprises in the range of from 20 to 50 percent by weight spherical cast tungsten carbide particles.

15. The rock bit of claim 12 wherein the filler comprises in the range of from 40 to 100 percent by weight spherical cast tungsten carbide particles.

B2  
Sub  
Ds  
16. The rock bit of claim 12 wherein the filler comprises spherical cast tungsten carbide particles having a particle size between about 100 to 200 mesh.

17. The rock bit of claim 12 wherein the filler comprises in the range of from 10 to 99 percent by weight spherical cast tungsten carbide particles having a particle size between about 80 to 200 mesh, and further comprises spherical cast tungsten carbide particles having a particle size between about 16 to 40 mesh.

18. The rock bit of claim 12 wherein the filler comprises in the range of from 10 to 99 percent by weight spherical cast tungsten carbide particles having a particle size between about 80 to 200 mesh, and further comprises tungsten carbide particles selected from the group including spherical cemented, crushed cemented, crushed cast and crushed macrocrystalline.

19. The rock bit of claim 18 wherein the filler further comprises macrocrystalline tungsten carbide particles having a particle size between about 40 to 80 mesh.

Sub D5  
20. A rock bit as recited in claim 12 wherein the hard-facing comprises in the range of from 10 to 90 percent by weight spherical cast tungsten carbide particles having a particle size between about 80 to 200 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 35 percent by weight of the filler material, the particles having a particle size in the range of from about 1 to 50 microns.

21. A rock bit as recited in claim 20 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical cast.

B2  
22. A rock bit as recited in claim 20 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

Sub D6  
23. A rock bit comprising:  
a body;  
at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone;

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising:

steel in the range of from 20 to 50 percent by weight;  
filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having a particle size between about 16 to 40 mesh and between about 80 to 200 mesh.

24. A rock bit as recited in claim 23 wherein the hard-facing comprises in the range of from 10 to 90 percent by weight spherical

Sub D6  
cast tungsten carbide particles having a particle size between about 16 and 40 mesh and between about 80 to 200 mesh, and further comprises ultra-fine tungsten carbide particles in the range of from 10 to 40 percent by weight of the filler material, the particles having a particle size in the range of from about 1 to 50 microns.

25. A rock bit as recited in claim 24 wherein the ultra-fine tungsten carbide particles are selected from the group consisting of carburized, macrocrystalline, and spherical cast.

26. A rock bit as recited in claim 24 wherein the steel in the hardfacing is dispersion strengthened by the ultra-fine tungsten carbide particles.

27. The rock bit of claim 23 wherein the filler comprises spherical cast tungsten carbide particles having a particle size between about 100 to 200 mesh.

Sub C17  
28. A rock bit comprising:  
a body;  
at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and  
a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,  
steel, and  
filler in the range of from 50 to 80 percent by weight,  
the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having a particle size less than 40 mesh.

Sub D7  
29. (Amended) A rock bit as recited in claim 28 [comprising steel in the range of 20 to 50 percent by weight] wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide particles having a particle size less than 40 mesh.

~~30. A rock bit as recited in claim 28 wherein the cast tungsten carbide particles have a particle size between about 16 to less than 40 mesh.~~

B Sub D8  
31. A rock bit as recited in claim 28 further comprising spherical tungsten carbide particles having a particle size between greater than 80 to 200 mesh.

Sub C2  
32. A rock bit comprising:  
a body;  
at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and  
a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,  
steel, and  
filler in the range of from 50 to 80 percent by weight,  
the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having a particle size greater than 80 mesh.

33. (Amended) A rock bit as recited in claim 32 [comprising steel in the range of 20 to 50 percent by weight] wherein the filler comprises in the range of from 19 to 100 percent by weight spherical cast tungsten carbide particles having a particle size greater than 80 mesh.

34. A rock bit as ~~recited in claim 32 wherein the cast tungsten carbide particles have a particle size between greater than 80 to 200 mesh.~~

Sub D9  
B2  
35. A rock bit as recited in claim 32 further comprising spherical tungsten carbide particles having a particle size between 16 to less than 40 mesh.

36. A rock bit comprising:

a body;

at least one cutting cone rotatably mounted to an end of the body, wherein the cone includes a gage surface at a heel portion of the cone; and

a number of teeth on the cone, the teeth including a plurality of inner row teeth and a plurality of gage row teeth located near a heel of each cone, wherein the teeth include a hardfacing comprising,

steel, and

filler in the range of from 50 to 80 percent by weight, the filler comprising in the range of from 10 to 100 percent by weight spherical cast tungsten carbide particles having a particle <sup>sizes</sup> size between about 16 to 40 mesh and between about 80 to 200 mesh.

37. A rock bit as recited in claim 36 comprising steel in the range of 20 to 50 percent by weight, and wherein the spherical tungsten carbide particles <sup>having</sup> ~~have a~~ particle <sup>sizes</sup> size between about 16 to less than 40 mesh and between greater than 80 to 200 mesh.